

D-Cure 357

Product description

D-Cure 357 is a modified nonylphenol-free cycloaliphatic amine curing agent. This curing agent is the low viscosity / less reactive version of D-Cure 358. Following the example of D-Cure 358, D-Cure 357 exhibits a good chemical and mechanical resistance and provides outstanding waterspot and carbamation resistance to the final system.

D-Cure 357 is used in combination with liquid epoxy resins in the formulation of two pack ambient curing systems. This product has been developed in particular for use in self levelling flooring applications as it provides outstanding waterspot resistance and excellent surface appearance to these floorings.

Product characteristics

Viscosity @25°C:	150 – 450 mPa.s
Gardner color:	≤ 1
Solids content:	100 % m/m
Hydrogen Equivalent Weight:	93 g/Eq
Specific gravity @20°C:	1.02 g/cm ³

System characteristics

phr with liquid resin (EEW 190):	50
Gel time @23°C:	30 - 35 minutes

Storage and handling

The product should be stored in a dry place, at room temperature.

Shelf-life: beyond 2 years, in original sealed containers.

More information about safe handling of this product can be found in the safety data sheet.

Disclaimer: this information is provided for general information purposes only and is believed to be accurate as of the date hereof; however QR Polymers B.V. does not make any warranties or representations of any kind regarding the information herein and no liabilities, including those for patent rights, can be derived from it. It is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use.